



Catálogo de Productos

Barracuda® Clase 6x19


- Alma de acero
- Galvanizado
- 6x19S
- 6x21F
- 6x25F
- 6x26WS




6x19S



6x21F



6x25F



6x26WS

Tabla de Resistencias a la tensión y Pesos (pulgadas)

Diámetro (pulgadas)	Peso Aproximado (lb/ft)	Resistencia a la Ruptura (lbs.)	
		Arado Mejorado	Arado Extramejorado
1/4	0.12	5,890	6,800
5/16	0.18	9,160	10,540
3/8	0.26	13,120	15,100
7/16	0.35	17,780	20,400
1/2	0.46	23,000	26,600
9/16	0.59	29,000	33,600
5/8	0.72	35,800	41,200
3/4	1.04	51,200	58,800
7/8	1.42	69,200	79,600
1	1.85	89,800	103,400
1 1/8	2.34	113,000	130,000
1 1/4	2.89	138,800	159,800
1 3/8	3.50	167,000	192,000
1 1/2	4.16	197,800	228,000
1 5/8	4.88	230,000	264,000
1 3/4	5.67	266,000	306,000
1 7/8	6.50	304,000	348,000
2	7.39	344,000	396,000

Normas de Referencia: ASTM-A-1-23; API 9A

Tabla de Resistencias a la tensión y Pesos (milímetros)

Diámetro (mm)	Peso Aproximado (kg/m)	Resistencia a la Ruptura (Toneladas Métricas)	
		Arado Mejorado	Arado Extramejorado

6.35	0.18	2.7	3.1
7.94	0.27	4.1	4.8
9.53	0.39	6.0	6.9
11.2	0.52	8.1	9.2
13	0.68	10.4	12.1
14.5	0.88	13.2	15.2
16	1.07	16.2	18.7
19	1.55	23.2	26.7
22	2.11	31.4	36.1
26	2.75	40.7	46.9
29	3.48	51.3	59.0
32	4.30	63.0	72.5
35	5.21	75.7	87.1
38	6.19	89.7	103.0
42	7.26	104.0	120.0
45	8.44	121.0	139.0
48	9.67	138.0	158.0
52	11.0	156.0	180.0
Normas de Referencia: ASTM-A-1-23; API 9A			
