



Catálogo de Productos

Tonina Clase 6x19


- Alma de Fibra
- Galvanizado
- 6x19S
- 6x21F
- 6x25F
- 6x26WS




6x19S



6x21F



6x25F



6x26WS

Tabla de Resistencias a la tensión y Pesos (pulgadas)

Diámetro (pulgadas)	Peso Aproximado (lb/ft)	Resistencia a la Ruptura (lbs.)	
		Arado Mejorado	Arado Extramejorado
1/4	0.11	5,480	6,020
5/16	0.16	8,520	9,370
3/8	0.24	12,200	13,420
7/16	0.32	16,540	18,200
1/2	0.42	21,400	23,600
9/16	0.53	27,000	29,800
5/8	0.66	33,400	36,600
3/4	0.95	47,600	52,400
7/8	1.29	64,400	70,800
1	1.68	83,600	92,000
1 1/8	2.13	105,200	115,600
1 1/4	2.63	129,200	142,200
1 3/8	3.18	155,400	171,000
1 1/2	3.78	184,000	202,000
1 5/8	4.44	214,000	236,000
1 3/4	5.15	248,000	274,000
1 7/8	5.91	282,000	312,000
2	6.72	320,000	352,000

Normas de Referencia: ASTM-A-1023; API 9A

Tabla de Resistencias a la tensión y Pesos (milímetros)

Diámetro (mm)	Peso Aproximado (kg/m)	Resistencia a la Ruptura (Toneladas Metricas)	
		Arado Mejorado	Arado Extramejorado

6.35	0.16	2.5	2.7
7.94	0.24	3.9	4.3
9.53	0.36	5.5	6.1
11.1	0.48	7.5	8.3
13	0.63	9.7	10.7
14.5	0.79	12.2	13.5
16	0.98	15.1	16.6
19	1.41	21.6	23.8
22	1.92	29.2	32.1
26	2.50	37.9	41.7
29	3.17	47.7	52.4
32	3.91	58.5	64.5
35	4.73	70.5	77.6
38	5.63	83.5	91.6
42	6.61	97.1	107.0
45	7.66	112.0	124.0
48	8.80	128.0	142.0
52	10.0	146.0	160.0
Normas de Referencia: ASTM-A-1023; API 9A			
